


Superimo 'ZF' 5000



TECHNICAL DATA SHEET

Basis

Chrysotile asbestos fibre, Natural Rubber and styrene butadiene rubber

General properties and applications :

To seal off wet steam, water, gases, alkaline chemicals and also suitable for oils & fuels under medium service conditions.

Dimensions of standard sheets :

Standard sheet sizes : 1500 mm X 1500 mm, 1500 mm X 4500 mm

Thickness: 0.25mm, 0.50mm, 0.75mm, 1mm, 1.5mm, 2mm, 3mm, 4mm, 5mm, 6mm (other sheet thickness on requirement).

Finish : Green / Greenco

Technical data

All data are typical values and refer to sheet thickness of 1.5 mm

	Specification	
Max. Operating Temperature		400°C
Max. Operating Pressure		80bar
Density	ASTM F 1315	1.95g/cm ³
Compressibility	ASTM F 36 A	8%
Recovery	ASTM F 36 A	45%
Tensile Strength	ASTM F 152	15N/mm ²
Stress Relaxation (50 N/mm ² , 16h, 300°C)	DIN 52913	18N/mm ²
Loss on ignition	ASTM F 495	24%
Thickness increase	ASTM F 146	
ASTM oil no.3 (5h, 150°C)		-
ASTM Fuel B (5h, 23°C)		-
Weight increase	ASTM F 146	
ASTM oil no.3 (5h, 150°C)		-
ASTM Fuel B (5h, 23°C)		-
Water (48h, 23°C)		6%

All information and recommendations given in this brochure are correct to the best of our knowledge.

However, in view of the wide variety of possible installation and operating conditions one cannot draw the final conclusion in all application cases regarding the behaviour in a gasket joint. Therefore, information can only serve as a guideline.